

CONFIRMATION

No. 30454111/CS/15.06.2026

In accordance with the VDI Guideline 2200 (edition June 2007) the gasket type



Deutsche
Akkreditierungsstelle
D-PL-12008-01-00

**KLINGER®top-chem 2003
DN40/PN40**

of the gasket manufacturer

**Rich. Klinger Dichtungstechnik GmbH & Co KG
Am Kanal 8-10, AT – 2352 Gumpoldskirchen**

was verified in a blowout safety test with the following test conditions:

initial gasket stress:	30	MPa
relating to ND40/PN40:	30.0	MPa
temperature of exposure:	100	°C
period of exposure:	48	h
remaining gasket stress:	14.4	MPa

Test step 1

test pressure (absolut):	60	bar
period of leakage measurement:	30	min

Test step 2

reduced gasket stress:	5	MPa
test pressure (absolut):	60	bar
period of leakage measurement:	40	min

In both test steps, the maximum permissible pressure drop and the maximum permissible leakage rate of 1 mg/(m·s) specified by VDI 2200 were not exceeded. The gasket thus meets the VDI 2200 requirements regarding blowout safety.

This confirmation is only valid in combination with the test report 30454116/-.

Lauffen, 15th June, 2026

amtec Advanced Measurement Messtechnischer Service GmbH

B. Eng. C. Six
Test Engineer

Dipl.-Ing. F. Herkert
Head of Laboratory